



CATALYST RESIN

PersaLyze™ CLT100

Catalyze Processes

SPECIFICATIONS

Matrix:	Crosslinked
Functional Group:	Sulfonic Acid
Physical Form:	Light brown beads
Ionic Form:	H ⁺
Moisture Content:	50 – 60 %
Particle Size:	310 – 1,250 μm
Particle Density:	1.20 g/mL
Bulk Density:	830 g/L (51.8 lb/ft ³)

Notes: The information and data are in good faith but without guarantee. Please consult our engineering team for more information before installing and operating the resin. Modifications of the specifications can occur without prior notice. IX resins should be stored in sealed bags in areas with a temperature above 0°C. See MSDS for safety issues.